

CARVER

by **Blanchon**
GROUP

STUCCO EXPRESS

Single-component, nitrosynthetic bonding agent

- ✓ Excellent filling
- ✓ Ideal for rapid cycles
- ✓ Excellent sanding performance
- ✓ Fast-fading odour

Cod. FO2055

Solvent-based, single-component, nitrosynthetic bonding agent to be mixed with fine wood dust for a fast-drying product that is easy to sand, for filling and skimming wood floors. Compared to classic solvent-based fillers, it has a weak odour that fades quickly. STUCCO EXPRESS is ready to use and does not require diluting.



APPLICATION

Sand the flooring with coarse- and medium-grain sandpaper. Prepare a smooth mix with STUCCO EXPRESS and the required amount of sawdust from the second sanding stage.

Apply the mix quickly with a wide stainless metal spatula, so that the highest amount possible penetrates into the cracks.

After the product has dried - this normally takes between 15 and 20 minutes, sand with fine paper and carefully vacuum up the dust.

Proceed to treatment using one of the Carver finishing cycles.

NOTICE

We recommend applying at room temperature between +15°C and +35°C with relative humidity between 35% and 75%.

During the application and drying stages, the work area must be properly ventilated.

Important: highly flammable product. Never smoke in the vicinity of or while handling the product.

We recommend using work gloves compliant with the EN374 standard.

TECHNICAL DATA

(with room temperature of +23°C and 65% relative air humidity)

Appearance	Transparent liquid
Viscosity	14" F8 ± 4" F8
Specific weight	0.84 ± 0.01
Dry to touch	10-15 minutes
Re-coat	15 minutes
Sanding	15 minutes
Complete drying	20 minutes
Average coverage per coat	8-12 m ² /litre
Tool cleaning	DILUENTE LAVAGGIO

Dispose of excess product and empty containers properly.

If the original unopened container is stored in a cool and dry place, the product will keep for at least 12 months.

N.B.: The information contained in this technical data sheet is correct to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.