

CARVER S.r.l.
Via Giovanni XXIII, 36
20090 Rodano (MI) ITALY
Tel. (02) 95.00171 (r.a.)
Fax (02) 95.320.921
internet: www.carver.it



TECHNICAL DATA SHEET

rev. 00 of January 21, 2014

WPC AQUAPRO (colored, impregnating product for wpc)

code IA1300XX

TECHNICAL DATA

(based on room temperature of 73.4°F and 65% of relative air humidity)

Viscosity	14" F4 ± 4" F4
Specific weight	1.02 ± 0.05
pH	8.0 ± 1.0
Dry to touch (dust dry)	20 min.
Recoating after / within	2 / 24 hr.
Completely dry	4 – 8 days
Recommended coverage per coat ♦	600-800 sq.ft /US gal.
Tools cleaning	IDROCLEANER
Thinning	ACQUA BLU
Max. allowed thinning rate	100 %
VOC %	5% ± 1%
Max. VOC content g/l	60 g/l
VOC limit value (Subcat. f WB Interior and exterior minimal build woodstain)	130 g/l

♦ depending on the wood species, on how abrading is effected and on the absorbed product amount.

DESCRIPTION

Water-based acrylic stain for staining and protecting WPC for both indoor and outdoor use. Protects the treated object against water and UV radiation. It can be used both for treatment of new WPC as well as restoration of tarnished WPC.

WPC AQUAPRO is available in various colours. All colours can be mixed together.

Standard packaging: 5 lt plastic can.

PREPARATION OF THE SUPPORTE

New WPC: wash with a solution of water and OUTDOOR DETER PRO, rinse thoroughly and allow to dry.

Tarnished WPC: apply our PULIDECK detergent with a brush and wait for at least 15-20 minutes. Remove the surface film with a semi-rigid brush or red Scotch Brite. Rinse with water and leave to dry (the film can also be removed with a pressure hose).

APPLICATION

When the support is dry, apply one of two coats of WPC AQUAPRO by brush, dabber or spray.

MAINTENANCE

For cleaning only, wash the WPC floor with a solution of water and OUTDOOR DETER PRO.

To restore a tarnished floor, treat it with PULIDECK as described above and proceed with a new treatment.

NOTICE

- In case of use in open sites, it is recommended not to apply the product in environments directly exposed to the sun and, in any case, to climatic conditions such as rain, snow or ice.
- Apply at a temperature between +15°C and +35°C with a relative humidity rate between 35% and 80%. Allow product to acclimatize before application.
- The colour tone can vary significantly depending on the type of WPC, its preparation, the method of application and the quantity of product applied. It is therefore recommended to perform a test before proceeding with the entire job.

Protect from freezing!

Dispose of excess product in authorized dumps!

If the original unopened container is stored in a cool and dry place, the product will keep for at least 12 months.

Obligation of manufacturer:

Technical datasheet and Safety datasheet are available for each Carver product. In case of products proved to be defective upon verification of manufacturer's persons in charge, manufacturer's only obligation shall be to replace such quantity of product proved to be defective or refund its purchase price. Neither the manufacturer nor its distributors shall be liable for any damage, loss or injury, direct or consequential, arising out of the use or the inability to use the product. The user shall ascertain the suitability of the product for the intended use. He is fully responsible for the correct application of the product in conformity with the local laws and regulations in force and undertakes all risk and liability connected therewith.